

Etamin-TH



Composición	100% Poliéster FR
Ancho	300 cm ± 2%
Largo de rollos	50 mts
	Etamin-TH: 90 gr/m ² ± 5%
	Etamin: 85 gr/m ² ± 5%
	Etamin 22/15: 75 gr/m ² ± 5%
	Etamin 22/25: 99 gr/m ² ± 5%
Peso	4-5
	EN ISO 105-B02:2014
Solidez a la luz	Método 2 escala 1-8; 8 mejor valor
	(B)
	EN ISO 12945-2:2000
Pilling	Escala A-D; A mejor valor
Encogimiento	Urdimbre: 1% · Trama: 1%
	UE: UNE EN 13773:2003 (C-1)
	F: NF P92-507:1995 (M-1)
	Consultar:
	A: B-1 DIN 4102 (B1)
Certificados ignífugos	I: C-1 UNI 9176:1998 (C-1)
	USA: NFPA 701
Igualdad color	El color puede variar de una partida a otra

Material	100% Polyester FR
Width	300 cm ± 2%
Roll length	50 mts
	Etamin-TH: 90 gr/m ² ± 5%
	Etamin: 85 gr/m ² ± 5%
	Etamin 22/15: 75 gr/m ² ± 5%
	Etamin 22/25: 99 gr/m ² ± 5%
Weight	4-5
	EN ISO 105-B02:2014
Light fastness	Method 2 scale 1-8; 8 best value
	(B)
	EN ISO 12945-2:2000
Pilling	Scale A-D; A best value
Shrinkage	Warp: 1% · Weft: 1%
	EU: UNE EN 13773:2003 (C-1)
	F: NF P92-507:1995 (M-1)
	Inquire:
	GER: B-1 DIN 4102 (B1)
Fire resistance certifications	I: C-1 UNI 9176:1998 (C-1)
	USA: NFPA 701
Colour matching	Colour may vary from batch to another



MADE IN
BARCELONA

